



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

VERIFICATION OF A TRANSLATION

I, the below named translator, hereby declare that:

My name and post office address are as stated below:

I am knowledgeable in the English language, and in the French language in which the below identified application was filed, and that I believe the annexed English translation of the certified copy of French Patent Application No. 01/13137 filed on 11th October 2001 to be a true and complete translation of the above identified application as filed.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that wilful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such wilful false statements may jeopardise the validity of the application or any patent issued thereon.

Alison Penfold

Date: 28th April 2006

Full name of the translator: Alison Winifred Penfold

Post Office address: Lloyd Wise
Commonwealth House
1-19 New Oxford Street
LONDON
WC1A 1LW
ENGLAND



FRENCH REPUBLIC

INPI - NATIONAL INSTITUTE OF INDUSTRIAL PROPERTY

PATENT OF INVENTION

CERTIFICATE OF UTILITY - CERTIFICATE OF ADDITION

OFFICIAL COPY

The Director-General of the National Institute of Industrial Property certifies that the attached document is a certified copy of an application for a deed of industrial property filed at the Institute.

Drawn up in Paris, 14th APR 2006

For the Director-General
of the National Institute of
Industrial Property
The Head of the Patents Section

(signature)

Martine PLANCHE

REGISTERED OFFICE

NATIONAL 26 bis, rue de Saint Petersburg
INSTITUTE OF 75800 PARIS Cedex 08
INDUSTRIAL Telephone: 33 (0)1 53 04 53 04
PROPERTY Fax: 33 (0)1 53 04 45 23
www.inpi.fr

NATIONAL PUBLIC INSTITUTION CREATED BY LAW NO. 51-444 OF 19th APRIL 1951



First filing

**INPI - NATIONAL INSTITUTE
OF INDUSTRIAL PROPERTY**26 bis, rue de Saint Pétersbourg
75800 Paris Cedex 08
Tel.: 01 53 04 53 04 Fax: 01 42 94 86 54**PATENT OF INVENTION
UTILITY CERTIFICATE**

Code of Intellectual Property – Book VI

REQUEST FOR GRANT 1/2

This form is to be filled in legibly in black ink

Reserved for INPI SUBMISSION OF ITEMS DATE 11/10/2001 PLACE 99 NATIONAL REGISTRATION NO. 0113137 ASSIGNED BY INPI DATE OF FILING ASSIGNED 11th OCT. 2001 BY INPI Your references for this file (optional) P10-1390/CHD/HS		1. NAME AND ADDRESS OF THE APPLICANT OR AGENT TO WHOM CORRESPONDENCE IS TO BE SENT Manufacture Française des Pneumatiques MICHELIN Christian DIERNAZ SGD/LG/PI – F35 - LADOUX 63040 CLERMONT-FERRAND CEDEX 09	
Confirmation of a filing by facsimile <input type="checkbox"/> No. assigned by INPI to the facsimile			
2. NATURE OF THE APPLICATION		Tick one of the following four boxes	
Patent application		<input checked="" type="checkbox"/>	
Application for a utility certificate		<input type="checkbox"/>	
Divisional application		<input type="checkbox"/>	
<i>Initial patent application</i>		No.	Date
<i>or initial application for a utility certificate</i>		No.	Date
Conversion of a European patent application <i>Initial patent application</i>		<input type="checkbox"/>	Date
3. TITLE OF THE INVENTION (200 characters or spaces maximum) Tread comprising incisions and lamella for moulding these incisions.			
4. DECLARATION OF PRIORITY OR REQUEST TO BENEFIT FROM THE DATE OF FILING OF A PRIOR FRENCH APPLICATION		Country or organisation Date No. Country or organisation Date No. Country or organisation Date No. <input type="checkbox"/> If there are other priorities, tick the box and use the "Continuation" form	
5. APPLICANT		<input checked="" type="checkbox"/> If there are other applicants, tick the box and use the "Continuation" form	
Name or company name		Société de Technologie MICHELIN	
First names			
Legal status		Société Anonyme (Limited Company)	
SIREN No.		414624379	
APE-NAF Code			
Address		Street 23 rue Breschet	
		Post code and town 63000 CLERMONT-FERRAND	
Country		FRANCE	
Nationality		French	
Telephone No. (optional)			
Fax. No. (optional)			
E-mail address (optional)			

**INPI - NATIONAL INSTITUTE
OF INDUSTRIAL PROPERTY**

First filing

**PATENT OF INVENTION
UTILITY CERTIFICATE**

REQUEST FOR GRANT 2/2

Reserved for INPI SUBMISSION OF ITEMS 11/10/2001 DATE PLACE 99 NATIONAL REGISTRATION NO. ASSIGNED BY INPI 0113137			
Your references for this file (optional)		P10-1390/CHD/HS	
6. AGENT			
Name			
First name			
Firm or company		Manufacture Française des Pneumatiques MICHELIN	
No. of permanent authorisation and/or of contractual relationship		PG 7107 and 7112	
Address	Street	23, place des Carmes Déchaux	
	Post code and town	63040	CLERMONT-FERRAND CEDEX 09
Telephone No. (optional)		04 73 10 78 34	
Fax. No. (optional)		04 73 10 86 96	
E-mail address (optional)			
7. INVENTOR(S)			
The inventors are the applicants		<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No In this case, provide a separate designation of inventor(s)	
8. SEARCH REPORT		Solely for a patent application (including divisional and conversion)	
Immediate		<input checked="" type="checkbox"/>	
or deferred		<input type="checkbox"/>	
Payment of the fee in instalments		Payment in three instalments, solely for individuals <input type="checkbox"/> Yes <input type="checkbox"/> No	
9. REDUCTION IN THE AMOUNT OF FEES		Solely for individuals <input type="checkbox"/> Requested for the first time for this invention (attach tax exemption certificate) <input type="checkbox"/> Requested prior to this filing (attach copy of the decision of acceptance for this invention or indicate the reference number thereof):	
If you have used the "Continuation" form, indicate the number of pages attached		1	
10. SIGNATURE OF THE APPLICANT OR AGENT (Name and position of the signatory) For MFPM – Agent 422-5/S.020 (signature) Christian DIERNAZ – MFPM employee		STAMP OF THE PREFECTURE OR INPI (signature) M. BLANCANEUX	

First filing

**INPI - NATIONAL INSTITUTE
OF INDUSTRIAL PROPERTY**

26 bis, rue de Saint Pétersbourg
75800 Paris Cedex 08
Tel.: 01 53 04 53 04 Fax: 01 42 94 86 54

**PATENT OF INVENTION
UTILITY CERTIFICATE**

Code of Intellectual Property – Book VI.

REQUEST FOR GRANT

Continuation page No. 1b / 2

<p>Reserved for INPI</p> <p>SUBMISSION OF ITEMS 11/10/2001</p> <p>DATE</p> <p>PLACE 99</p> <p>NATIONAL REGISTRATION NO.</p> <p>ASSIGNED BY INPI 0113137</p>

This form is to be filled in legibly in black ink

Your references for this file (optional)		P10-1390/CHD/HS	
4. DECLARATION OF PRIORITY		Country or organisation	
OR REQUEST TO BENEFIT FROM		Date	No.
THE DATE OF FILING OF		Country or organisation	No.
A PRIOR FRENCH APPLICATION		Date	No.
5. APPLICANT			
Name or company name		MICHELIN Recherche et Technique S.A.	
First names			
Legal status		Société Anonyme (Limited Company)	
SIREN No.			
APE-NAF Code			
Address	Street	Route Louis Braille 10 et 12	
	Post code and town	1763	GRANGES-PACCOT
Country		SWITZERLAND	
Nationality		Swiss	
Telephone No. (optional)			
Fax. No. (optional)			
E-mail address (optional)			
5. APPLICANT			
Name or company name			
First names			
Legal status			
SIREN No.			
APE-NAF Code			
Address	Street		
	Post code and town		
Country			
Nationality			
Telephone No. (optional)			
Fax. No. (optional)			
E-mail address (optional)			
10. SIGNATURE OF THE APPLICANT OR AGENT		STAMP OF THE	
(Name and position of the signatory)		PREFECTURE OR INPI	
For MFPM – Agent 422-5/S.020 (signature)		(signature)	
Christian DIERNAZ - MFPM employee		M. BLANCANEUX	

Law No. 78-17 of 6th January 1978 relating to computers, files and liberties applies to the answers given on this form. It guarantees you the right of access and correction for the data relating to you at the INPI.

The invention relates to the field of tread patterns for tyres. It relates more particularly to the incisions moulded in the treads and the moulding elements used for moulding such incisions.

5 In the context of improving the performances of its tyres, the applicant company has filed several patents in which various geometries of incisions are described which, while creating additional ridges which are indispensable for cutting the film of water covering the roadway, make it possible to limit the loss of rigidity of the tread due to the presence of these incisions. For example, US Patent 4794965 describes a specific arrangement of incisions in a zigzag within the thickness of a tread; US Patent 5783002 describes an incision the opposing walls of
10 which are provided with motifs in relief intended to fit into one another when passing into the imprint with the roadway. These various incisions ensure mechanical cooperation of the walls of rubber mix which is very appreciable for reducing the relative movements between said walls.

The development of vehicles using new driving aid systems (wheel anti-locking system when
15 braking, anti-skid system, stability control system) mean that the requirements in terms of the performance of tyres have changed.

For these vehicles, there has been discovered a need for a tyre having a tread provided with a plurality of incisions to form a plurality of ridges intended to come into contact with the roadway, these incisions having a new geometry which, while limiting the reduction in overall
20 rigidity of this tread under high shearing stresses, has the ability to reduce as far as possible the relative movements between the opposed walls once they are in at least partial contact with each other under low shearing stresses (and very particularly in rainy weather or when the roadway is wet).

In the known prior art, there are documents which state the advantage of producing on the walls
25 of the incisions areas of roughness having specific dimensions. For example, the Japanese document published under the number 96/175115 advocates a roughness of between 20 and 300 microns.

However, it was demonstrated that merely these areas of roughness were insufficient to achieve a good compromise under all conditions of use of these tyres.

30 To meet this need, the tyre according to the invention comprises a tread having a running surface intended to be in contact with the roadway during travel of said tyre. This tread is provided with a plurality of incisions extending into the thickness of the tread, each incision of

average thickness e being defined by facing walls of rubber mix, each incision having an average surface S_m defined as being the location of the points substantially at the same distance from the walls defining said incision, this tread being characterised in that at least one of the walls defining each incision comprises:

5 at least one series of lines of motifs in relief relative to said wall and having a maximum height measured perpendicular to said wall at least equal to $1/10$ of the width e , each series of lines comprising a plurality of lines substantially parallel to each other,

and in that at least one of the walls defining each incision comprises:

10 over its entire surface, a plurality of elements in relief regularly distributed over said wall and forming on this wall surface an average roughness of between $1/100$ and $1/10$ of the width e of the incision.

Preferably, there is formed, on at least one wall, a first series and a second series of lines of motifs in relief the maximum height of which, measured perpendicular to said wall, is at least equal to $1/10$ of the width e , the lines of the first series intersecting the lines of the second series. Advantageously, the lines of the first series form with the lines of the second series an
15 acute angle of at least 45° .

In this manner, it is possible to obtain a tread the overall rigidity of which is relatively undisturbed by the presence of the incisions according to the invention and which comprises a large number of ridges. The incision according to the invention makes it possible, with one and
20 the same rubber material, to increase substantially the equivalent coefficient of friction of the walls of the parts of rubber mix defining said incision. This increase in coefficient of friction is particularly effective in reducing the slight movements of one wall relative to the opposite wall and in particular close to the surface of contact with the roadway. The combined presence of lines in relief (comparable to macro-level roughness) and of surface roughness (comparable to
25 micro-level roughness) unexpectedly increases the locking effect of one wall on the facing wall mainly in the range of low or medium stresses.

Another advantage obtained is that the tyre provided with incisions according to the invention is less sensitive to the presence of water on the roadway, the dominating influence of which on the coefficient of friction between two smooth walls of one and the same rubber mix is known (a
30 reduction of said coefficient which may be as much as 50%, or even more).

The invention is used in treads for tyres of passenger vehicles or of heavy vehicles; in each respective case, the values of the areas of macro-level roughness and areas of micro-level

roughness may be readily adapted as a function of the average widths of the incisions, which may be as much as 3 mm.

Preferably, the lines of motifs in relief of each series of at least one wall are substantially inclined by an angle β of between 10° and 80° with a direction perpendicular to the running surface of the tread, and this over at least part of their length.

Another subject of the invention relates to a lamella intended for fitting in a tread mould of elastomeric material, this lamella comprising main faces for moulding in a tread facing walls defining an incision of average thickness e , at least one of the main faces of the lamella comprising at least one series of lines of hollowed motifs relative to said wall and having a maximum depth measured perpendicular to said wall at least equal to $1/10$ of the width e , each series of lines of motifs comprising a plurality of lines substantially parallel to each other, at least one of the main faces of the lamella comprising over its entire surface an equivalent average roughness of between $1/100$ and $1/10$ of the width e of the incision.

"Line of hollowed motifs" may mean a continuous line or a line formed of discontinuous motifs. Preferably, at least one main face of the lamella according to the invention is provided with a first series and a second [series of] lines of hollowed motifs, the lines of each series extending in one and the same direction, and the lines of the first series intersecting the lines of the second series to form an average acute angle α at least equal to 45° .

Other characteristics and advantages of the invention will become apparent from the description given hereafter with reference to the appended drawings, which show, by way of non-limitative example, forms of embodiment of the invention.

In these drawings:

Figure 1 shows a metal lamella used for moulding an incision according to the invention;

Figure 2 shows a sectional view along the line II-II through the lamella shown in Figure 1;

Figure 3 shows a rubber wall of an incision according to the invention produced in a tread.

First filing

- 4 -

In Figure 1, there can be seen a lamella 1 of plane overall geometry comprising two main faces 2, 2' intended for moulding the facing walls defining an incision according to the invention in a tread. The thickness of the lamella measured between the two main faces is equal in the case described to 0.6 mm. The average surface of this lamella is here a plane surface dividing the
5 lamella into two parts of the same volume and extending at half-thickness.

Over all of each main face 2 and 2', a surface treatment by shot blasting has been carried out in order to obtain on the walls of rubber material moulded with the lamella a uniform micro-level roughness of between 1/10 and 1/100 of the thickness of the lamella. This surface treatment produces a plurality of cavities 3 and 3' regularly distributed over the main faces of the lamella,
10 said cavities having in the present case a maximum depth of between 40 and 50 μm . These cavities 3 and 3' are visible more particularly in Figure 2, which shows a view in section along the line II-II of the lamella 1.

Furthermore, two series 3, 4 of substantially rectilinear grooves 31, 41 have been formed on each main face 2 and 2' of the lamella 1. The grooves 31 of the first series 3 have a triangular
15 cross-section and have a maximum depth of 0.1 mm and a maximum width of 0.5 mm; these grooves 31 are, in the present case, rectilinear and parallel to each other and distant from each other by an average pitch equal to 1 mm. The average pitch between the grooves is preferably at least equal to 5% of the average length L_1 of the incision and at most equal to 20% of this same length L_1 (this length L_1 , which in the present case is equal to 20 mm, being measured parallel
20 to a direction parallel to the running surface of a tread moulded in a mould provided with said lamella).

In the case described, the grooves 31 of the wall 2 form an angle β equal to 25° with a direction perpendicular to the running surface of the tread (this direction is perpendicular to the direction in which the length L_1 is measured).

25 The grooves 41 of the second series 4 on the same main face 2 have the same characteristics as those of the first series and intersect the latter, forming an average acute angle α equal to 45° .

The series of grooves produced on the other main face 2' of the lamella have characteristics similar to those which have just been described. It is of course possible to produce on the second main face grooves having different orientations from those produced on the first main
30 face in order to improve still further the interaction between the facing faces of the incision moulded with this lamella.

The grooves formed on the main faces of the lamella result in moulding of ribs (in relief) on the walls defining the incision moulded with said lamella; it will be considered here that these series of ribs form an area of macro-level roughness.

5 It was observed that the combination of micro-level roughness with macro-level roughness (as defined in the present specification) makes it possible to achieve better balance during travel, whether in the field of low stresses or of medium stresses.

Figure 2, which represents a view in section of the lamella 1 along the line II-II, shows the profiles in section of the grooves 31 and 31': the latter are substantially triangular. On the other hand, the area of micro-level roughness formed by the plurality of cavities 3 and 3' is visible on
10 the main faces 2 and 2', including on said grooves.

Furthermore, provision may be made for the incisions to have average surfaces the geometric forms of which are appropriate to permit mechanical cooperation by interleaving of the opposing walls defining said incisions. This mechanical cooperation offers the advantage of taking over the locking obtained with the areas of micro-level and macro-level roughness
15 according to the invention as the stresses increase substantially.

Figure 3 shows a wall 20 of an incision according to the invention, this incision being moulded in a tread pattern block 10 of a rubber tread. This wall of width 20 [sic] comprises undulations 11 about a direction X perpendicular to the length L of the incision (this direction extends within the thickness of the tread pattern block 10), said undulations extending over this entire
20 length L. These undulations are formed on the facing walls defining the incision and permit mechanical meshing of one wall on the other when passing into contact with the roadway. Furthermore, the wall 20 comprises a combination of areas of micro-level and macro-level roughness (the latter being in the form of ribs represented diagrammatically by the lines 310 and 410).

25 In the case described with reference to Figure 3, the areas of micro-level roughness are identical to those obtained by moulding with the lamella described with the support of Figure 1.

The combination of the mechanical meshing by the presence of undulations, of the areas of micro-level roughness and the areas of macro-level roughness as defined here imparts to the tyre provided with a tread according to the invention performances which are improved still further
30 and in particular during the implementation of the wheel anti-locking or anti-skid system.

First filing

- 6 -

The invention is not limited to the examples described and shown, and various modifications can be made thereto without departing from the scope thereof. For example, the series of reliefs moulded on the walls defining an incision may have, viewed projected on to a plane surface tangent to one of the walls, non-rectilinear traces in particular of circular forms whether
5 concentric or not, zigzag forms, undulating forms, etc.

Equivalently, the lines of reliefs may be formed of sections of lines forming sorts of discontinuous lines, the space between each section being less than the average length of said sections.

CLAIMS

- 5 1. A tread made of elastomeric material for tyres, this tread being provided with a plurality of incisions, each incision of average width e and of average surface S_m being defined by facing walls (20), this tread being characterised in that at least one of the walls (20) defining each incision comprises at least one series of lines of motifs in relief (310, 410) relative to said wall (20) and having a maximum height measured perpendicular to said wall at least equal to $1/10$ of the width e , and in that at least one of the walls defining each incision furthermore comprises over its entire surface an average roughness of between $1/100$ and $1/10$ of the width e of the incision.
- 10 2. A tread of elastomeric material for tyres according to Claim 1, characterised in that at least one of the walls (20) defining each incision comprises:
- 15 at least a first series and a second series of lines of motifs in relief (310, 410) relative to said wall and having a maximum height measured perpendicular to said wall at least equal to $1/10$ of the width e , each series of lines comprising a plurality of lines extending in the same direction, the lines of the first series intersecting the lines of the
- 20 second series.
3. A tread according to Claim 2, characterised in that the lines (310) of the first series form with the lines (410) of the second series an average acute angle α at least equal to 45° .
- 25 4. A tread according to one of Claims 1 to 3, characterised in that the average surface S_m of at least one incision has a non-planar geometry appropriate so that the walls defining said incision are capable of cooperating mechanically with each other when passing into contact with the roadway, in order to reduce the movements of one wall relative to the other.
- 30 5. A tread according to Claim 4, characterised in that the average surface S_m comprises at least one undulation (11) in the direction perpendicular to this average surface.

6. A tread according to one of Claims 1 to 5, characterised in that the lines in relief (310, 410) of at least one wall (20) are inclined by an angle β of between 10° and 80° with a direction perpendicular to the running surface of the tread.
- 5 7. A tread according to one of Claims 1 to 6, characterised in that the average pitch between the lines (310, 410) of each series of lines in relief is at least equal to 5% of the length L of the incision and at most equal to 20% of this same length L.
8. A lamella (1) intended for fitting in a tread mould of elastomeric material, this lamella
10 comprising main faces (2, 2') for moulding in a tread facing walls defining an incision of average thickness e, at least one of the main faces of the lamella comprising at least one series (3, 4) of lines of motifs (31, 41, 31', 41') forming hollows relative to said wall and having a maximum depth measured perpendicular to said wall at least equal to 1/10 of the width e, each
15 one of the main faces of the lamella comprising over its entire surface an equivalent average roughness of between 1/100 and 1/10 of the width e of the incision.
9. A lamella (10) intended for fitting in a tread mould according to Claim 8, characterised in that each main wall (2, 2') of the lamella is provided with a first (3) and a second (4) plurality of
20 lines of hollowed motifs regularly distributed over said wall, the hollowed motifs (31, 41, 31', 41') having a depth at least equal to 1/10 of the width e, the lines of motifs (31, 31') of the first series intersecting the lines (41, 41') of the second series, forming an acute angle at least equal to 45° .
- 25 10. A lamella (1) intended for fitting in a tread mould according to Claim 8 or Claim 9, characterised in that furthermore motifs in relief (11) are formed on each main wall of said lamella, the motifs in relief (11) of one wall being complementary with the motifs in relief of the other wall in order to permit mechanical cooperation of the walls defining the incision moulded with said lamella, this mechanical cooperation limiting the relative movements of the
30 facing walls.